

C. BOGMANS

CMHR SCHUIMEN

CMHR	KLEUR	DENSITEIT (kg/m ³)	HARDHEID (ILD) N	DRUKWEERSTAND (CLD) kPa
CMHR 27 SOFT	BEIGE	27	80	2.0
CMHR 35 MED	GRIJS	35	140	3.4
CMHR 40 MED	ABRIKOOS	40	150	3.8
CMHR 50 SOFT	ROZE	50	145	3.6
CMHR 50 MED	WIT	50	170	4.2
CMHR 60 SOFT	BLAUW	60	110	2.9
CMHR 60 MED	WIT	60	220	5.2

CMHR-CME	KLEUR	DENSITEIT (kg/m ³)	HARDHEID (ILD) N	DRUKWEERSTAND (CLD) kPa
CMHR 28 MED	LICHT BRUIN	28	130	3.3
CMHR 30 EXTRA	LICHT GEEL	30	180	4.5
CMHR 35 HARD	BEGIE	35	140	3.6
CMHR 39 HARD	SAHARA	39	155	3.9
CMHR 46 HARD	ROZE	46	260	6.5
CMHR 60 EXTRA	GRIJS	60	300	8.0