

C. BOGMANS

TRADITIONELE POLYETHERSCHUIMEN

V-Polyether	KLEUR	DENSITEIT (kg/m ³)	HARDHEID (ILD) N	DRUKWEERSTAND (CLD) kPa
SG 16 MED	WIT	16	95	2.2
SG 17 SOFT	WIT	17	48	1.2
SG 17 MED	WIT	17	95	1.7
SG 20 SOFT	WIT	20	60	1.5
SG 20 HARD	WIT	20	115	2.8
SG 20 EXTRA	LICHT BLAUW	20	140	3.5
SG 24 EXTRA	CITROENGEEL	23	230	6.0
SG 25 SOFT	WIT	25	90	2.0
SG 25 MED	GRIJS	25	110	2.7
SG 25 EXTRA	LICHT BLAUW, WIT, BEIGE	25	180	4.5
SG 29 MED	GROEN	29	152	3.8
SG 30 MED	WIT	30	120	3.0
SG 30 HARD	WIT	30	180	4.5
SG 30 EXTRA	DONKER BLAUW	30	200	5.0
SG 30 SUPER	WIT	30	240	6.0
SG 35 HARD	BLAUW	35	200	5.0
SG 35 EXTRA	WIT	35	260	6.5
SG 40 SOFT	LICHT GROEN	40	116	2.9
SG 40 MED	GEEL	40	180	4.5
SG 40 HARD	WIT	40	220	5.5
SG 40 EXTRA	WIT	40	280	7.0
SG 46 EXTRA	WIT	46	320	8.0
SG 65 EXTRA	GRIJS	65	490	11.7

High Resilience (HR)	KLEUR	DENSITEIT (kg/m ³)	HARDHEID (ILD) N	DRUKWEERSTAND (CLD) kPa
SG 23 MED	WIT	23	55	1.3
SG 25 MED	AZURE	25	70	1.7
SG 30 SOFT	KAKI	30	90	2.1
SG 30 MED	LICHT BLAUW	30	125	3.0
SG 35 PLUSH	GEEL	35	51	1.5
SG 35 SOFT	LICHT GEEL	35	110	2.7
SG 35 MED	GEEL	35	140	3.5
SG 35 HARD	GEEL	35	180	4.2
SG 40 SOFT	BLAUW	40	116	2.9
SG 40 MED	ABRIKOOS	40	165	4
SG 43 HARD	WIT	43	190	4.7
SG 45 SOFT	WIT	45	90	2.5
SG 45 MED	BLAUW	45	150	3.8
SG 45 HARD	ROZE	45	215	5.5
SG 50 SOFT	LICHT GEEL	50	125	3.0
SG 50 MED	LICHT BRUIN	50	150	3.8
SG 50 HARD	GRIJS	50	260	6
SG 55 MED	GRIJS	55	148	3.7
SG 60 SOFT	GEEL	60	90	2.5